

## Data sheet Murdotec 1000U green

- good wear resistance
- good sliding properties
- good shock and impact absorption
- very good anti-adhesion properties

**Applications:** transportation and conveyor technology (chain and belt drives)

Technical properties	(PE-UHMW 1000U green)	Values	Units	DIN	ISO/EC
Colour		green			
Molecular weight			g/mol		
Code					15527:2013
Density		≤0,96	kg/dm <sup>3</sup>	53479	1183
Water absorption – saturation at 23°C		<0,01	%	53715	
<b>Mechanical properties</b>					
Yield/ break stress		~20	MPa	53455	527-2
Breaking elongation		>280	%	53455	527-2
Coefficient of elasticity (pulling test)		>700	MPa	53457	527-2
Notch impact strength - Charpy		≥80	kJ/m <sup>2</sup>	53453	179
Shore hardness D		61-65	°	868	7619-1
Ball hardness		>30	N/mm <sup>2</sup>	53456	2039
Sand-Slurry-Test		120	%		15527
Coefficient of sliding friction Steel (0,25m/s, 0,25N/mm <sup>2</sup> )		-0,2	μ		
Coefficient of sliding friction POM (0,25m/s, 0,25N/mm <sup>2</sup> )					
<b>Thermal properties</b>					
Heat conductivity 23°C		0,4	W/(K x m)	52612	
Linear thermal coefficient of expansion α (average value between 23 und 60 °C)		20x10 <sup>-5</sup>	m/(K x m)	53752	11359-2
Upper service temperature in air	short term	90	°C		
	constant (5000h)	80	°C	53446	
Lower service temperature		-150	°C		
Burning behavior per UL 94 – sample thickness 3/6 mm		HB			
Melting Point		130-135	°C		3146 method C
<b>Electrical properties</b>					
Electrical strength		≤45	kV/mm	53481	60243
Specific constant resistance		>10 <sup>12</sup>	Ω x cm	53482	60093
Surface resistance		>10 <sup>12</sup>	Ω	53482	60093
<b>Physiological properties</b>					
Approved for use in food industry (FDA)		No			
Approved for use in food industry (EU)		No			

The values, shown in this table, enable to compare materials faster. These values are short-term values, which can be influenced by processing, environmental as well as application conditions. Therefore, these values do not represent assured properties. It is due to the customer's responsibility whether the chosen material is suitable for its specific application.

Status 01/2017

**Murdotec Kunststoffe GmbH & Co. KG · Heßlingsweg 8 · 44309 Dortmund (Brackel) · Phone: +492314257798-0 · Fax: +492314257798-29**

Geschäftsführer: Detlev Höhner, Dipl.-Ing. (FH) Josef Ikemann  
 Rechtsform: Kommanditgesellschaft  
 Sitz: Dortmund · Registergericht Dortmund, HRA 14026

Persönlich haftende Gesellschafterin:  
 Murdotec Kunststoffe Beteiligungs mbH  
 Sitz: Dortmund · Registergericht Dortmund, HRB 14610

http:// [www.murdotec.de](http://www.murdotec.de)  
 E-Mail: [info@murdotec.de](mailto:info@murdotec.de)